



# Extreme S-308

## EXTREME SignWelder™ Signboard Adhesive

### Product Description

**Extreme S-308** is a medium viscosity, **solvent-free** structural adhesive system that provides flexibility, toughness and surface adhesion for bonding plastics and metals in any combination. Cured performance shows excellent adhesion and bond strength to nylons, polystyrenes, fiberglass, reinforced plastics, stone, ceramics and most plain and plated metal components. This material can withstand thermal cycling and shock loading between dissimilar materials.

Although it is always best to clean and prepare most bonded surfaces for improved adhesion. **Extreme S-308** will work successfully in many applications **without preparation**.

**Extreme S-308** is moderate cure speed, two-component product with an open time of 5 - 8 minutes at 23° C after thorough mixing. For a longer open time consider product number **Extreme S310**.

### Why Should You Select This Adhesive?

- Toughness and Durability
- Excellent Adhesion to Plastics And Metals
- Impact Resistance
- Peel Strength
- 100% Reactive Solids Formulation for VOC compliance and safety
- Fast Cure Speed And Excellent Gap Cure

Contact an **EXTREME ADHESIVES®** Adhesive Applications Specialist for further recommendations on adhesive selection.

### Physical Properties

#### Typical Uncured Properties (LIQUID)

Applies to both adhesive and activator sides

Viscosity	50,000cps mixed
Specific Gravity	1.01 (20/20C°)
Color	white
Flashpoint	51°F (COC method)
Toxicity	moderate, see MSDS
Solvents	none
Mix Ratio	1 : 1
Fillers	yes
Clean Up Solvents	MEK, Acetone

#### Typical Cured Properties (SOLID)

typical film thickness 0.030".

Shore D Hardness	75
Adhesive Testing on	Plastics, glass filled nylon, styrene, ABS, PVC
Thermal Service Range	-65°F to 260°F
Chemical Resistance	excellent
Elongation	60%
Impact Resistance	20 ftlbs/in <sup>2</sup> on steel
Peel Strength	20-25 psi on aluminum
Lap Shear Strength	2340 psi - as rec'd CRS 3390 psi – aluminum 3365 psi grit blasted steel

### Instructions For Use

Combine resin and activator in equal volume and mix thoroughly. For convenience and accuracy use pre-measured cartridges with disposable static mixers. Open time is 5 minutes at room temperature. Handling strength within approximately 10-15 minutes.

### Shelf Life

Shelf Life is at least 6 months when properly stored in an unopened original container in a cool, dark area at least 55°F to 75°F.

The properties represented herein are TYPICAL VALUES and not intended for use in specifications. **Extreme Adhesives, Inc.** MAKES NO EXPRESS OR IMPLIED WARRANTIES OF MERCHANTABILITY, FITNESS OR OTHERWISE. While the information presented is believed to be accurate, no warranty or recommendation is made as to application. Determination of product suitability is the sole responsibility of the user. Suggestions made do not constitute any guarantee in as much as use conditions are beyond our control.